

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMOND AND COLORED STONES EDUCATIONAL PROGRAMS

ELECTRONIC COPY

DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

| | NUMBER 134464457 | | | | | | MUMBAI, November 28, 2014 | | | | | | | | | | |
|---|--|--------|---------------------|---|---|----|---------------------------|--|-----|-----------------|-----|-------------|---|----------------|----------------|----------------|--|
| | LABORATORY REPORT (ORIGINAL) | | | | | | TO WHOM IT MAY CONCERN. | | | | | | | | | | |
| DESCRIPTION SHAPE AND CUT | NATURAL DI ROUND BRIL | | | | The symbols do not usually reflect the size of the characteristics. Red symbols indicate internal characteristics. Green symbols indicate external characteristics. | | | | | | | | | | | | |
| CARAT WEIGHT COLOR GRADE CLARITY GRADE CUT GRADE POLISH | 0.60 CARAT H VS 1 EXCELLENT | | | | | | | Å | | | | | | | | | |
| SYMMETRY Measurements Table Size | VERY GOOD 5.37 - 5.44 x 3.30 mm 61.5% | | | | | | | | | | | | | 7 | | | |
| Crown Height - Angle Pavilion Depth - Angle Girdle Thickness | 13.5% - 34.8° 43% - 40.9° SLIGHTLY THICK (FACETED) | | | | | | | insignificant external details, visible under high magnification only, are not shown | | | | | | | | | |
| Culet Total Depth FLUORESCENCE | POINTED 61.3% NONE | | | | | | | | | | | > | l | | Jan | In | |
| | LUORESCENCE NONE Cemologist (07) | | | | | | | | | | | | | | | JSC (01) | |
| | | | | | | | | | | | | | | | | | |
| | CLARITY GRADE: | Interr | Internally Flawless | | | δŋ | VVS | 2 | VSl | vs ₂ | SI1 | SI | 2 | I ₁ | I ₂ | I ₃ | |
| | | | | | | | | | | | | | | | | | |
| | COLOR GRADE : | D | E F | G | н | t. | J K | L | М | N C | P | Q | R | S - Z | FANCY | COLOR | |

PROPORTIONS - MARGIN: ± 1% MEASUREMENTS - MARGIN: ± 0.02mm

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This report is subject to the terms and conditions set forth above and on reverse.

© I.G.I., 2000, edition 2010

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute