

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMOND AND COLORED STONES EDUCATIONAL PROGRAMS

## **ELECTRONIC COPY**

## DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

	NUMBER 189576379			MUMBAI, January 18, 2016								
	LABORATORY		)	TOW	HOM IT N	IAY CONC	ERN.					
DESCRIPTION SHAPE AND CUT CARAT WEIGHT COLOR GRADE CLARITY GRADE CUT GRADE POLISH SYMMETRY Measurements	NATURAL DIAMOND ROUND BRILLIANT 0.40 CARAT J SI 1 GOOD VERY GOOD GOOD 4.56 - 4.59 x 2.99 mm			<text><text><text><image/><text><text><text></text></text></text></text></text></text>								
Table Size Crown Height - Angle Pavilion Depth - Angle Girdle Thickness Culet Total Depth FLUORESCENCE	51.5% 18% - 36.6° 42% - 40° THICK TO VE POINTED 65.5% NONE											
	CLARITY GRADE:	Internally Flawless	vvs <sub>1</sub>	vvs <sub>2</sub>	VS1	VS <sub>2</sub>	SI	SI <sub>2</sub>	ŋ	<sup>1</sup> 2	I <sub>3</sub>	

PROPORTIONS - MARGIN: ± 1%	
MEASUREMENTS - MARGIN: ± 0.02m	m

Е F G

COLOR GRADE : D

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

М

Ν

0

Р

Q

R

S - Z

FANCY COLOR

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

## This report is subject to the terms and conditions set forth above and on reverse.

н 1 J Κ E.

## © I.G.I., 2000, edition 2010

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute