

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMOND AND COLORED STONES EDUCATIONAL PROGRAMS

## **ELECTRONIC COPY**

## DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

	NUMBER 2	04642425		MU	IUMBAI, March 22, 2016						
	LABORATORY		1	TO W	'HOM IT N	1AY CONC	ERN.				
DESCRIPTION SHAPE AND CUT	NATURAL DI. ROUND BRIL			,	Red	do not usual! symbols indi n symbols inc	cate intern	al charact	eristics.	ristics.	
CARAT WEIGHT COLOR GRADE CLARITY GRADE CUT GRADE	0.50 CARAT J VS 1 EXCELLENT			K		X					
POLISH SYMMETRY Measurements Table Size	EXCELLENT EXCELLENT 5.06 - 5.08 x 3 56%	3.18 mm		K							
Crown Height - Angle Pavilion Depth - Angle	14.5% - 33° 44.5% - 41.6°					nsignificant <b>ex</b> Nigh magnific					
Girdle Thickness Culet Total Depth FLUORESCENCE	MEDIUM POINTED 62.6% NONE				 0-		aper and additi	document are ho	t listed,	Gemolo	June of the second seco
					inc		, <del></del>	any security slu	na di Go		
	CLARITY GRADE:	Internally Flawless	VVS <sub>1</sub>	VVS <sub>2</sub>	VS1	vs <sub>2</sub>	SI	SI2	l <sub>1</sub>	<sup>1</sup> 2	l <sub>3</sub>

CLARITY GRADE:	Internally Flawless			VVS1			vvs <sub>2</sub>	vs <sub>2</sub> vs <sub>1</sub>		vs <sub>2</sub>		SI	SI2		ų.	<sup>1</sup> 2	13	
COLOR GRADE :	D	E	F	G	Н	I.	J	К	L.	М	Ν	0	Ρ	Q	R	S - Z	FANCY	COLOR
PROPORTIONS - MARGIN: ± 1% MEASUREMENTS - MARGIN: ± 0.02mm																		

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

## This report is subject to the terms and conditions set forth above and on reverse.

## © I.G.I., 2000, edition 2010

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute