

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMOND AND COLORED STONES EDUCATIONAL PROGRAMS

DR-CTB-A-05-2012

ELECTRONIC COPY

DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

	NUMBER 214639	MUMBAI, May 4, 2016									
	LABORATORY REPORT (ORIGINAL)			TO WHOM IT MAY CONCERN.							
			21-21			ls do not usually				eristics.	
DESCRIPTION				Red symbols indicate internal characteristics. Green symbols indicate external characteristics.							
SHAPE AND CUT	ROUND BRILLIANT	Choin	*								
CARAT WEIGHT	2.00 CARAT										
COLOR GRADE	Gundian										
CLARITY GRADE	SI 2										
CUT GRADE	GOOD										
POLISH	VERY GOOD										
SYMMETRY	GOOD										
-											
Measurements	7.78 - 7.85 x 5.05 m	m									
Table Size	58.5%										
Crown Height - Angle	16.5% - 38.4°			insignificant external details, visible under high magnification only, are not shown							
Pavilion Depth - Angle	43% - 40.7°										
Girdle Thickness	SLIGHTLY THICK T (FACETED)			<	\bigcirc	>>		_			
Culet	POINTED			Jamentin							
Total Depth	64.6%										
FLUORESCENCE	NONE Gemologist (01)										ist (01)
LASERSCRIBE	IGI 214639416										
LASERSURIDE	IGI 214039410										
	CLARITY GRADE: Inter	nally Flawless	10/6-	VVS ₂	VS ₁	1/2-	Q1_	SI-	Ĩ.		
	CLARIT GRADE, INIGH	nuily Fluwiess	VVS1	v v 32	voj	VS ₂	SI	SI ₂	η	¹ 2	13
	COLOR GRADE : D	E F G	н і	J K	L M	N O	Ρ	Q R	S - Z	FANCY C	COLOR
	Proportions - Margin: ± Measurements - Margin:										
	The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical										

phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This report is subject to the terms and conditions set forth above and on reverse.

© I.G.I., 2000, edition 2010

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute