

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMOND AND COLORED STONES EDUCATIONAL PROGRAMS

ELECTRONIC COPY

DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

	NUMBER 2		MUMBAI, April 20, 2016									
	LABORATORY)	TO W	'HOM IT M	IAY CONC	ERN.					
DESCRIPTION SHAPE AND CUT	NATURAL DI ROUND BRIL			The symbols do not usually reflect the size of the characteristics. Red symbols indicate internal characteristics. Green symbols indicate external characteristics.								
CARAT WEIGHT	0.40 CARAT				\bigwedge			1				
COLOR GRADE	к				$\langle \rangle$	\times	\searrow	$\langle \rangle$		/ >		
CLARITY GRADE CUT GRADE	VS 1 VERY GOOD			K				$\langle \rangle$				
POLISH	VERY GOOD				$\overline{\mathbf{N}}$	4 4	\mathbf{X}			\leq		
SYMMETRY	VERY GOOD			Ŕ	$ \land$	\square					\neq	
Measurements	4.85 - 4.87 x 2	2.77 mm				X	<i>Y</i>					
Table Size	61.5%											
Crown Height - Angle	11.5% - 31.1°				in	isignificant e x	ternal deta	ails, visible u	Inder			
Pavilion Depth - Angle	42% - 40.1°				h	igh magnific	ation only,	are not sh	nown			
Girdle Thickness	MEDIUM TO	SLIGHTLY THICK										
Culet	POINTED							<u> </u>		\frown		
Total Depth	56.9%									han	The	
FLUORESCENCE	NONE						191		11	Gemolog	gist (01)	
					0-7 tha	Security features watermarked p t, as a composite	aper and addit	document are ho ional features no stry security sta	ot listed,			
	CLARITY GRADE:	Internally Flawless	VVS ₁	VVS ₂	VSI	vs ₂	SI	SI2	I ₁	l ₂	l ₃	

PROPORTIONS - MARGIN: ± 1% MEASUREMENTS - MARGIN: ± 0.02mm

E

F G

COLOR GRADE : D

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

М

Ν

0

Р

Q

R

S - Z

FANCY COLOR

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This report is subject to the terms and conditions set forth above and on reverse.

Н 1 J Κ E.

© I.G.I., 2000, edition 2010

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute