

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMOND AND COLORED STONES EDUCATIONAL PROGRAMS

ELECTRONIC COPY

DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

	NUMBER 208612369	MUMBAI, May 19, 2016								
	LABORATORY REPORT (ORIGINAL)	TO WHOM IT MAY CONCERN.								
DESCRIPTION SHAPE AND CUT	NATURAL DIAMOND ROUND BRILLIANT	The symbols do not usually reflect the size of the characteristics. Red symbols indicate internal characteristics. Green symbols indicate external characteristics.								
CARAT WEIGHT	0.70 CARAT									
COLOR GRADE	(YPD) 이 것 ! YPD) 이 것 !									
	SI 2									
CUT GRADE	VERY GOOD									
POLISH	EXCELLENT									
SYMMETRY	GOOD									
Measurements	5.65 - 5.73 x 3.52 mm									
Table Size	58%									
Crown Height - Angle	15% - 35.4°	insignificant external details, visible under high magnification only, are not shown								
Pavilion Depth - Angle	43.5% - 41.2°	high thag inication only, are not shown								
Girdle Thickness	THIN TO SLIGHTLY THICK (FACETED)									
Culet	POINTED									
Total Depth	61.8%	Junti								
FLUORESCENCE	NONE	Gemologist (01)								
		Om Security features included in this document are hologram, watermarked paper and additional features not listed, that, as a composite, exceed industry security standards.								

																		8425K
CLARITY GRADE:	Inte	ərnally	Flawle	ess	V	/VS1		vvs ₂		VSl	VS	⁵ 2	SI	S	l ₂	IJ	¹ 2	l ₃
COLOR GRADE :	D	E	F	G	Н	t	J	К	L	М	Ν	0	Ρ	Q	R	S - Z	FANCY	COLOR
ROPORTIONS - MAI MEASUREMENTS - MA																		

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This report is subject to the terms and conditions set forth above and on reverse.

© I.G.I., 2000, edition 2010

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute