

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMOND AND COLORED STONES EDUCATIONAL PROGRAMS

ELECTRONIC COPY

DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

	NUMBER 224639197	MUMBAI, July 21, 2016							
	LABORATORY REPORT (ORIGINAL)		TO WHOM IT MAY CONCERN.						
DESCRIPTION SHAPE AND CUT	NATURAL DIAMOND ROUND BRILLIANT		ТІ	Red	s do not usually d symbols indic en symbols indic	ate internal cl	haracteristics.		
CARAT WEIGHT COLOR GRADE CLARITY GRADE CUT GRADE POLISH SYMMETRY Measurements Table Size	0.74 CARAT I INTERNALLY FLAWLESS EXCELLENT EXCELLENT 5.73 - 5.80 x 3.61 mm 56.5%		Insignificant external details, visible under high magnification only, are not shown						
Crown Height - Angle Pavilion Depth - Angle	15.5% - 35.3° 43.5% - 41°								
Girdle Thickness Culet Total Depth	MEDIUM (FACETED) POINTED 62.4%					Z		Juni	tim
FLUORESCENCE	NONE			-	Security features in	cluded in this docum		Gemologist	t (01)
COMMENTS LASERSCRIBE	IDEAL CUT ROUND BRILLIANT IGI 224639197				, macaumi reduuesi na watermaiked pap nat, as α composite,	per and additional fe	patures not listed,		
	CLARITY GRADE: Internally Flawless	VVS1	vvs ₂	VS1	vs ₂	SI ₁ S	⁶¹ 2 ¹ 1	1 ₂	I ₃
	COLOR GRADE : D E F G	H I	JKL	М	N O	PQ	R S-Z	FANCY CO	LOR
	PROPORTIONS - MARGIN: ± 1%								

MEASUREMENTS - MARGIN: ± 0.02mm

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This report is subject to the terms and conditions set forth above and on reverse.

© I.G.I., 2000, edition 2010

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute